



627C ALL WEATHER PVC CEMENT MEDIUM BODY / FAST SET

PART NUMBER	SIZE	MASTER QTY	LBS. PER CASE	UPC CODE
627C-3	Pint	12	14	671436257681
627C-4	Quart	12	27	671436257698
627C-5	Gallon	6	52	671436257704

DESCRIPTION

627C is a solvent cement designed specifically for use in joining all types of PVC (Poly Vinyl Chloride) pipe and fittings with interference fit through 6" diameter schedules 40 and 4" diameter schedule 80. 627C is suitable for all-weather use and remains fluid and usable in cold weather to -15°F and in hot weather to 110°F. It is a fast setting, high strength PVC Cement. 627C meets 'LOW-VOC' requirements, as outlined by SCAQMD 1168/316A.

APPLICATION

627C is formulated for use on piping systems for potable water, DWV (drain, waste, vent), electrical conduit, irrigation and sewer/drain applications.

627C is manufactured to the high standard of ASTM D 2564 to ensure a quality product. A sample is kept from each batch to verify the quality of LSP cements. This product is manufactured in the U.S.A.

Follow the directions on can label. Additional information is available upon request. Skill and knowledge on the part of the user is required to make a good quality joint.



3689 Arrowhead Drive, Carson City, NV 89706 Phone (800) 854-3215 Fax (800) 243-1777

E-mail sales@lspproducts.com Website www.lspproducts.com

Content matter is subject to change at any time. It is the user's responsibility to ensure the most updated revisions are obtained

SAFETY PRECAUTIONS

EXTREMELY FLAMMABLE. Do not use or store near heat, sparks or flame. Use only in well ventilated area. Keep container closed when not is use. Avoid prolonged breathing of vapor. Avoid contact with skin and eyes. In case of skin or eye contact, flush repeatedly with water. Get medical attention if irritation persists. If swallowed, drink water, do NOT induce vomiting and call a physician. Keep out of reach of children.

TECHNICAL DATA

PRODUCT	BODY	COLOR	DENSITY	SET TIME
627C	Medium	Clear	7.6 lb/gal	Fast

MAX VOC PER SCAQMD 1168/316A: 510 G/L

SPECIFICATIONS: ASTM D 2564, SCAQMD 1168/316A

HYDROSTATIC PRESSURE TEST: 400 psi min. (73° F, 2 hour cure)

FLASH POINT: -4° F (closed cup) SHELF LIFE: 3 year minimum

LISTINGS:





Product Submittal				
Job Name:				
Date:				
Part Number	Quantity			
Architect:				
Contractor:				

